



1 PRODUCT NAME

STYROFOAM™ 2.0 pcf Spray Polyurethane Foam Insulation

2 Manufacturer

The Dow Chemical Company
Building & Construction
200 Larkin
Midland, MI 48674
1-866-583-BLUE (2583)
Fax 1-989-832-1465
www.dowstyrofoam.com/architect
www.insulateyourhome.com

3 Product Description

STYROFOAM™ Spray Polyurethane Foam (SPF) Insulation is a two-component spray-applied polyurethane foam insulation that creates a seamless, monolithic barrier for protection against water and air. The SPF blend successfully incorporates the Enovate 3000 blowing agent from Honeywell.

BASIC USE

STYROFOAM™ SPF Insulation is created from a unique polyol technology, which offers improved foam yield and wide processing latitude. Offered in two formulations for both new and retrofit applications, STYROFOAM SPF Insulation expands during installation to fill cavities, cracks and crevices, preventing uncontrolled air leakage and maintaining consistent, comfortable indoor temperatures. The closed-cell, 2.0 pcf foam serves as both an insulation and air sealant for a

wide range of applications throughout the building envelope. In addition, STYROFOAM SPF Insulation resists moisture and provides structural reinforcement for improved racking strength.*

SIZES

STYROFOAM™ SPF Insulation is sold in 55 gal drum sets (one A isocyanate and one B polyol blend; total 950 lb). Contact your Dow sales representative with questions.

4 Technical Data

APPLICABLE STANDARDS

Applicable test methods include:

- ASTM C1029 – Standard Specification for Spray-Applied Rigid Cellular Polyurethane Thermal Insulation
- ASTM C518 – Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- ASTM D1621 – Standard Test Method for Compressive Properties of Rigid Cellular Plastics
- ASTM D1622 – Standard Test Method for Apparent Density of Rigid Cellular Plastics
- ASTM D6226 – Standard Test Method for Open Cell Content of Rigid Cellular Plastics

CODE COMPLIANCES

STYROFOAM™ SPF Insulation complies with the following codes:

- Conforms to IRC requirements for foam plastic insulation; see ASTM C1029
- Underwriters Laboratories, Inc. and Intertek Research Report (UL) Classified Class I at 4 inches; see UL 723
- ABAA standards for air leakage per ASTM E283

Contact your Dow sales representative or local authorities for state and local building code requirements and related acceptances.

*STYROFOAM SPF Insulation provides structural enhancement only. Use in conjunction with approved structural components and framing members consistent with following local building code requirements.

PHYSICAL/CHEMICAL PROPERTIES

STYROFOAM™ SPF Insulation exhibits typical physical properties as indicated in Table 1 when tested as represented.

ENVIRONMENTAL DATA

STYROFOAM™ SPF Insulation is chlorofluorocarbon (CFC) free and uses the Enovate 3000 blowing agent from Honeywell, which is a zero ozone-depleting product.

FIRE PROTECTION

STYROFOAM™ SPF Insulation is organic and combustible and may constitute a fire hazard. Do not expose foam to flame or temperatures above 240°F.

5 Installation

Only personnel trained in spray polyurethane foam application should install STYROFOAM™ SPF Insulation.

STYROFOAM SPF Insulation contains isocyanate, hydrofluorocarbon blowing agent and polyol. Read the Material Safety Data Sheet carefully before use. Wear protective clothing, gloves, goggles and proper respiratory protection. Supplied air or an approved air-purifying respirator equipped with an organic vapor sorbent and a particle filter is required to maintain exposure levels below applicable ACGIH, OSHA or WEEL limits. Provide adequate ventilation.

Spray equipment must be capable of delivering the proper ratio (1:1 by volume) of polymeric isocyanate and polyol blend at

TABLE 1
Typical Physical Properties⁽¹⁾ of STYROFOAM™ SPF Insulation

Property and Test Method	Value	
	STYROFOAM™ SPF Insulation 3062 35°F-80°F (35°F-100°F) Ambient (Substrate) Processing	STYROFOAM™ SPF Insulation 3049 60°F-100°F (60°F-120°F) Ambient (Substrate) Processing
Core Density, ASTM D1622, lb/ft ³	>2	>2
Compressive Strength, ASTM D1621, lb/in ² , parallel	26	26.4
Tensile Strength, ASTM D1623, lb/in ² , parallel	55	53.3
Closed-cell Content, ASTM D6226	94	96
Thermal Conductivity, ASTM C518, k-factor ⁽²⁾	0.154	0.154
Thermal Resistance, ASTM C518, R-value per inch ⁽³⁾	6.5	6.5
Water Vapor Permeability, ASTM E96, perm-inch	1.1	1.4
Water Absorption, ASTM D2842, % by volume	3.2	3.2
Dimensional Stability, ASTM D2126, % volume change		
At -20°F, 14 days	<1.0	<1.0
At 200°F, 14 days	<1.0	<1.0
At 158°F, >98% R.H.	<4.0	<3.3
Surface Burning Characteristics ⁽⁴⁾ , ASTM E84, 4" thickness (Intertek UL 723)		
Flame spread	<25	20
Smoke developed	400	<350

(1) Not to be considered sales specifications.

Properties determined by processing foam with Gusmer H2O/35 primary heater at 120°F (A,B), hose temperature of 120°F with GX7 gun; .028 drilled module with 70 PCD; dynamic pressures at 600 psi-1,000 psi.

(2) Initial value. Aged k-factor: 0.185 at 180 days, 50% R.H. per FTC requirements.

(3) Initial value. Aged R-value: 5.4 at 180 days, 50% R.H. per FTC requirements.

(4) Calculated flammability values for this or any other material are not intended to represent hazards that may be present under actual fire conditions.

adequate temperatures and spray pressures. Substrate must be at least 5 degrees above dew point, with best processing results when ambient temperature humidity is below 80 percent. Substrate must also be free of moisture (dew or frost), grease, oil, solvents and other materials that would adversely affect the adhesion of the polyurethane foam. Substrate temperatures should not exceed 120°F for STYROFOAM SPF 3049 (commonly referred to as "Summer" formula) and 100°F for STYROFOAM SPF 3062 (commonly referred to as "Fall/Spring" formula).

Due to the exothermic reaction of the isocyanate and polyol blend, mixed components should be applied in layers (maximum 2-1/2" thickness per layer). Allow foam to cool completely before applying successive layers.

Contact a local Dow representative or access the literature library at www.dowstyrofoam.com/architect or www.insulateyourhome.com for more specific instructions.

6 Availability

STYROFOAM™ SPF Insulation is distributed through an extensive network. For more information, call 1-800-232-2436.

7 Warranty

Not applicable.

8 Maintenance

STYROFOAM™ SPF Insulation has a shelf life of six months when stored dry between 60°F and 90°F. Avoid direct sunlight during shipping and storage on the job site.

Caution should be exercised when opening containers as pressure may be present when material has been exposed to elevated temperatures.

Empty drums are non-returnable and should be disposed of by using current industrial practices in accordance with federal, state or local regulations.

9 Technical Services

Dow can provide technical information to help address questions when using STYROFOAM™ SPF Insulation. Technical personnel are available to assist with any insulation project. For technical assistance, call 1-866-583-BLUE (2583).

10 Filing Systems

- www.dowstyrofoam.com/architect
- www.insulateyourhome.com
- www.sweets.com

IN THE U.S.:

- For Technical Information: **1-866-583-BLUE (2583)**
- For Sales Information: **1-800-232-2436**

THE DOW CHEMICAL COMPANY

• Building & Construction • 200 Larkin • Midland, MI 48674 • www.dowstyrofoam.com/architect • www.insulateyourhome.com

NOTICE: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

COMBUSTIBLE: Protect from high heat sources. Local building codes may require a protective or thermal barrier. For more information, consult MSDS, call Dow at 1-866-583-BLUE (2583) or contact your local building inspector. In an emergency, call 1-989-636-4400.

STYROFOAM™ SPF Insulation contains isocyanate, hydrofluorocarbon blowing agent and polyol. Read the Material Safety Data Sheet carefully before use. Wear protective clothing, gloves, goggles and proper respiratory protection. Supplied air or an approved air-purifying respirator equipped with an organic vapor sorbent and a particle filter is required to maintain exposure levels below applicable ACGIH, OSHA or WEL limits. Provide adequate ventilation.

Building and/or construction practices unrelated to building materials could greatly affect moisture and the potential for mold formation. No material supplier including Dow can give assurance that mold will not develop in any specific system.

a proud partner of

